



KUT PLAST MF

Superplasticising, Water Reducing, Strength Accelerating Admixture

ADM – 07 - 0104

DESCRIPTION

KUT PLAST MF is a super plasticising concrete admixture based on melamine formaldehyde. It can be used to either produce flowing concrete or enable large water reductions to be made for the same workability. In addition, it has the advantage of producing very high early strengths and thus makes the material suitable for use in precast concrete applications and in areas where higher workability concrete and fast shutter stripping are required.

ADVANTAGES

KUT PLAST MF provides the following benefits:

As a super plasticiser :

- Substantial improvements in workability without increased water or the risk of segregation.
- Normal set without retardation, even if accidentally overdosed.
- Improved concrete density and surface finish.

As a water reducer :

- Up to 30% water reduction 40% increase in 28 days strengths are possible.
- High strengths after 8 hours and double 16 hours strengths can be obtained.
- Increases frost and water resistant properties of the concrete because of reduced water contents and low permeability.
- Extremely high workability, little or no vibration required.
- Can replace steam curing.
- Faster mould turn ground.
- High durability concrete.
- Ultra-high strength concrete.
- Idle for power trowelled floors.

STANDARDS

KUT PLAST MF complies with **BS-5075, 1982** and **ASTM - C494, Type F**.

TECHNICAL DATA

Form	: Liquid
Colour	: Colourless to straw yellow
Specific gravity	: 1.10
Chloride content	: Nil to BS 5075
Effect, on Setting	: Little effect even after overdosing
Freezing Point	: -5° C
Storage	: Protect from frost
Suitability	: All Portland cements including SRC
Sulphate Content	: Less than 0.3

INSTRUCTIONS FOR USE

In order to obtain the best results, **KUT PLAST MF** must be used with specifically designed mixes for the particular requirements of strength, cost saving or flowing concrete. For maximum dispersion, **KUT PLAST MF** should be added with the mixing water. On no account should it be added to the dry cement. Where concrete is being delivered by ready mixed trucks, then **KUT PLAST MF** should be added at site, the mixer drums should then be rotated at maximum revolution until a uniform mix is achieved.

Dosage : The optimum dosage for **KUT PLAST MF** should be determined by site trials with the particular concrete mix under prevailing ambient conditions.

0.30 - 0.50 litres/50 kg cement, for flowing concrete.
0.70-1.00litre/50 kg cement for high strength concrete

But dosage can be as low as 0.15 litres/50 kg to as high as 1.5 litres/50 kg depending on the needs and requirements of concrete involved.

Overdosing : An over dose of double the intended amount of **KUT PLAST MF** will result in very high workability and some retardation. The ultimate compressive strength of the concrete will not be impaired if cured properly.

Curing : As with all structural concrete, normal curing methods apply.



Specialities Construction
Chemicals Factory

Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait, Tel: +965 4565165 - 4565145 Fax: +965 4565135
Email: technical@aspeckuwait.com



PACKAGING

KUT PLAST MF is supplied in 20 and 210 litre drums.

Cleaning : Spillages of **KUT PLAST MF** can be removed with water.

Storage : **KUT PLAST MF** should be protected from extremes of temperature. Should the material become frozen, it must be completely thawed and thoroughly mixed before use. **KUT PLAST MF** has a minimum shelf life of 12 months provided temperature is 5° C to 30° C.

PRECAUTIONS

HEALTH AND SAFETY

KUT PLAST MF is non-toxic. Any splashes to the skin should be washed immediately with water. Splashes to the eyes should be washed immediately with water and medical advice should be sought.

Fire : **KUT PLAST MF** is non-flammable.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor: