



KUT PLAST WP1

Water Proofing Admixture For Paving Blocks, Tiles And Bricks

ADM – 17 - 0104

DESCRIPTION

KUT PLAST WP1 is a specially designed blend of surface active waterproofing aids and integral synergistically active chemicals. **KUT PLAST WP1** helps achieve the desired water tightness in paving blocks, tiles and bricks with its dual action by reducing mix water requirements and migration of its surface active ingredients towards the surface.

ADVANTAGES

- Powder form makes it easy to use in semi dry mixes.
- Reduced water demand, makes product more denser, giving reduced water permeability and increased strength.
- Water Proofing: Provides better dispersion of cement particles giving closer packing and reduces pore size. This results in minimised capillary action in concrete. The surface active ingredients migrate towards the surface and impart good to excellent water repellancy properties.
- Water absorption is reduced upto 40% against control mix due to the dual action of water reduction and water repellancy.
- Chloride free: No added chlorides.
- Compatibility with Cements: Can be used with all types of portland cements including sulphate resisting cement.

USES

KUT PLAST WP1 is recommended to be used in paving blocks, tiles and bricks manufacturing. It can be used in the sand lime brick mix. It can also be used in high strength blocks such as Interlock, Paving Blocks, Kerbstones etc.

KUT PLAST WP1 provides good degree of water tightness and water repellent properties to tiles and bricks. It is highly recommended for controlling or eliminating efflorescence in tiles and bricks which are laid on damp or moist substrates.

TYPICAL PROPERTIES

- Calcium chloride content: Nil to **BS 5075 : 1982**.
- Air entrainment: Less than 1% additional air is entrained.
- Setting time: Less than 1 hour retardation at normal dosage.
- Cement Compatibility: Compatible with sulphate resisting and other portland cements.
- Admixture Compatibility: Use as single admixture only. For special requirements contact **ASPEC** Technical Department.
- Water Proofing: Reduction of water absorption by 25 to 40% as per **ASTM C 642**.

INSTRUCTIONS FOR USE

KUT PLAST WP1 should be premixed in dry mix prior to addition of water. Water, cement ratio should be reduced typically by 10 to 15% of original but can be adjusted as per mix requirements.



Specialities Construction
Chemicals Factory

Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait, Tel: +965 4565165 - 4565145 Fax: +965 4565135
Email: technical@aspeckuwait.com



Dosage : KUT PLAST WP1 should be added at a rate of 1 kg per 50 kg of cement, optimum dosage should be determined by site mixes with actual site conditions.

Overdosing : An overdose of double the recommended amount of KUT PLAST WP1 will result in some retardation and increased workability. The ultimate compressive strength of concrete will not be significantly effected.

Curing : As per standard practices.

TECHNICAL SUPPORT

'ASPEC' provides technical support service to mix design, admixture selection, evaluation of trials etc. Please contact the Technical Department in these cases.

PACKAGING

KUT PLAST WP1 is supplied in 25kg bags.

STORAGE - KUT PLAST WP1 should be protected from extremes of temperature. KUT PLAST WP1 has a minimum shelf life of 12 months provided temperature is kept within the range 2° C to 30° C.

Fire : KUT PLAST WP1 is non flammable.

HEALTH & SAFETY

KUT PLAST WP1 is non-toxic. Any splashes to the skin should be washed immediately with water and medical advice should be sought.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor: