



# KUT PLAST EPG

## Plasticised Expanding Grout Admixture

ADM – 20 - 0104

### DESCRIPTION

**KUT PLAST EPG** is supplied as a powder admixture. The material is a combination of a plasticising agent and a gas producing expansion medium. The plasticising agent allows the use of a reduced water / cement ratio with consequent increased strengths and durability. The expansive medium counteracts the natural settlement and plastic shrinkage of the grout and adds stability and cohesion. Sufficient restrained expansion is developed to ensure a high degree of interfacial contact. For Non - Shrink concrete mixes, the plasticization effect of **KUT PLAST EPG** is minimal, hence suitable superplasticiser, water reducer or retarder should be used when appropriate.

### USES

**KUT PLAST EPG** is an admixture for cementitious grouts where a reduced water / cement ratio and positive expansion is required. Applications include bed grouting, duct grouting, non-shrink concrete infilling & jointing.

### ADVANTAGES

- Gaseous expansion system compensates for plastic shrinkage and settlement in properly designed cementitious grout.
- Reduced water / cement ratio in the grout mix ensures low permeability and long term durability in service.
- Gives high grout fluidity with low water / cement ratio, thus making placement or injection of the grout easy.
- No metallic iron content to corrode and cause staining and deterioration due to rust expansion in the grout.
- Composition allows high early strength development in grouts, without the use of chlorides.

### STANDARDS

**KUT PLAST EPG** is a suitable pre-stressing grout admixture when complying with **BS 8110 Part 1, 1985, Section 8.9.4.6.**

### TECHNICAL DATA

- **Chloride Content** : Nil to **BS 5075**
- **Compressive Strength** : **KUT PLAST EPG** allows reduction of the water / cement ratio of cementitious grouts whilst maintaining flow properties. This gives improvement in strength and long term durability when cured under restraint.
- **Setting Times** : **KUT PLAST EPG** does not significantly affect the setting times of cement based grouts.
- **Expansion Characteristics** : The controlled positive expansion in unset grouts incorporating **KUT PLAST EPG** overcomes plastic settlement when measured in accordance with **ASTM C827**. An unrestrained expansion of up to 4 % is typical.
- **Time For Expansion** : 15 minutes to 2 hours. Temperatures above 20° C may slightly reduce these times.
- **Compatibility** : **KUT PLAST EPG** is compatible with all types of portland cements. **KUT PLAST EPG** may be used in mixes containing certain other **ASPEC** admixtures. Consult **ASPEC** for further information.

### INSTRUCTIONS FOR USE

#### MIXING :

#### Grouts

For best results a mechanically powered grout mixer must be used. For quantities up to 50 kg. a slow speed drill fitted with a high shear paddle is suitable. Larger quantities will require a high shear vane mixer.



Specialities Construction  
Chemicals Factory

Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait, Tel: +965 4565165 - 4565145 Fax: +965 4565135  
Email: technical@aspeckuwait.com



It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity. The selected water content should be accurately measured into the mixer. Slowly add cement (and sand if required) and **KUT PLAST EPG**. Mix continuously for 5 minutes, making sure that a smooth even consistency is obtained.

### Concrete

For dry mixing process add **KUT PLAST EPG** with cement. For wet mixing process, add **KUT PLAST EPG** prior to placement and mix for 3 to 5 minutes before casting.

### APPLICATION

Areas to be grouted should be prepared to ensure substrates are clean, sound and then pre-wetted. The unrestrained surface area of the grout must be kept to a minimum. Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Adopt usual placing or pumping procedures ensuring a continuous operation.

### Dosage

OPC	Concreting Sand	Water	KUT PLAST EPG	Approx. Yield
50 kg.	-	20-22 ltr.	250 g	36 litres
50 kg.	50 kg.	22-24 ltr.	250 g	57 litres

**Note :** For grout, mortar or non - shrink concrete mixes with an aggregate / cement ratio more than 1, use 4 x 250 g units of **KUT PLAST EPG** per 100 kg. of cement.

### Effects of Overdosing

Drastic overdosing of **KUT PLAST EPG** increases expansion and may cause frothing.

### Curing

On completion of the grouting operation, any exposed areas which are not to be cut back should be thoroughly cured by means of water application. **KUT CURE** curing compounds or wet hessian.

### Cleaning

Grouts with **KUT PLAST EPG** should be removed from tools and equipment with clean water immediately after use. Remove cured material mechanically with **ASPEC's KUT ACID ETCH**.

### LIMITATIONS

**KUT PLAST EPG** is incompatible with high alumina cement.

### PACKAGING

**KUT PLAST EPG** is supplied in packs containing 24 x 250 g units and in 5 kg. and 25 kg. bags.

### CAUTION

When using 5 kg. & 25 kg. bags, the proportioning for each mix has to be done by using a weighing balance, and the balance material in the bag should be closed tightly after use as the material is highly hygroscopic.

### STORAGE

**KUT PLAST EPG** has a shelf life of 12 months if kept in dry store in its original packaging. High temperature and humidity storage may reduce this period.

### PRECAUTIONS

#### HEALTH & SAFETY

**KUT PLAST EPG** is of low hazard. Contact with skin and eyes, or inhalation of dust should be avoided. Wear suitable protective clothing, gloves, eyes / face protection and dust masks. After contact with skin, wash off with clean water. In case of contact with eyes, rinse immediately with plenty of water and seek medical attention.

**ASPEC** endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

**Distributor:**